

**Obtaining strength-ductility combination in a laser additive manufactured (FeCoNi)<sub>86</sub>Al<sub>7</sub>Ti<sub>7</sub> high-entropy alloy at cryogenic temperature**

Xie, K.; Fang, Y.; Ma, P.; Yang, H.; Wan, S.; **Prashanth, Konda Gokuldoss**; Gargarella, P.; Mu, Y.; Wang, G.; Jia, Y. Journal of materials research and technology 2025 / p. 819-831 <https://doi.org/10.1016/j.jmrt.2024.12.125>